

Blue LC EP-2

Typical Properties

NLGI Grade	2
Thickener Type	Lithium/Complex
Texture	Smooth/Buttery
Color	Blue
Worked Penetration, ASTM	
D-217, 77AF, 60 Strocks	265-295
Dropping Point, ASTM	
D-2265, AF (ACE) Min	500 (260)
Rust & Corrosion, ASTM	
D-1743	Pass
Mobility Testing, LT-37, 45° F	17.54 grams/minute
Timkin, ASTM D-2509,	
OK Load, Lbs.	65
Four Ball EP, ASTM D-2596	
Weld Point Kg,	800
Four Ball EP,ASTM D-2666	
L.W.I.	120
Base Fluid Properties	
Flash Point °F	500 Min.
cSt @ 100° C	127-157
Pour Point,° F	+25