

MOLY EP 2 Lubricating Grease

Typical Properties

NLGI Grade	2
Soap Type	Lithium
Texture	Smooth
Color	Moly Gray
Worked Penetration, ASTM	
D-217, 77AF, 60 Strocks	265-295
Dropping Point, ASTM	
D-2265, ° F Min	350
Oxidation Stability, ASTM	
D-942, psi Drop 100 Hrs. Max	10
Rust & Corrosion, ASTM	
D-1743	Pass
Water Washout, ASTM	
D-1264, 175° F, Max	10%
Timkin, ASTM D-2509,	
OK Load, MIN	40
Four Ball EP, ASTM D-2596	
Weld Point Kg,	250
Four Ball Wear,ASTM D-2666	
Scar Dia. mm, 40kg,	0.60
Base Oil Viscosity	
SUS @ 100° F	900-1100
cSt @ 100° C	15.5-17.5
cSt @ 40° C	180-210
Viscosity Index	88
Pour Point °F	0