

# TACKY OGL EP 11

## Typical Properties

NLGI Grade	1H
Thickener Type	Calcium/Lithium Based
Texture	Smooth/Tacky
Color	Black
Worked Penetration, ASTM	
D-217, 77AF, 60 Strocks	290-320
Dropping Point, ASTM	
D-2265, ° F Min	325
Rust & Corrosion, ASTM	
D-1743	Pass
Mobility Testing, LT-37, 45° F	17.54 grams/minute
Timkin, ASTM D-2509,	
OK Load, Lbs.	65
Four Ball EP, ASTM D-2596	
Weld Point Kg,	800
Four Ball EP,ASTM D-2666	
L.W.I.	120
<b>Base Fluid Properties</b>	
Flash Point °F	500 Min.
cSt @ 100° C	127-157
Pour Point,° F	+25